



Test Report

No.T32120220769SN

Date: Feb 19, 2021

Page 1 of 2

FILT

SR629-34 BUILDING, DOSAN-DAERO 229, GANGNAM-GU, SEOUL, KOREA

The following samples were submitted and identified by/on behalf of the client as:

ETIQA AIRWAY ROUND BASIC MASK A (LARGE) (PURPLE)

Case No. : CA321202236809
SGS Ref No. : AYHA21-01212
Lot No. / Batch Code : NOT PROVIDED
Sample Description : PURPLE MASK
Sample Receiving Date : JAN 29, 2021
Testing Period : JAN 29, 2021 - FEB 19, 2021

Test Requested	Conclusion
Splash resistance (ISO 22609:2004)	PASS

***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****

Signed for and on behalf of
SGS Hong Kong Ltd.

Au Kam Chi, Gigi
Technical Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



Test Report

No.T32120220769SN

Date: Feb 19, 2021

Page 2 of 2

Test Results:

Splash resistance (ISO 22609:2004)

Test Side : Purple colour (Outside)
 Pre-Conditioning : Minimum of 4 hours at 21±5°C and 85±5% R.H.
 Test Condition : 21±5°C and 85±5% R.H.
 Test Pressure : 16.0 kPa (120 mmHg)
 No of Test Specimen Tested : 32
 No of Test Specimen Passed : 32


Test Specimen #	Synthetic Blood Penetration
1-32	None Seen

Note:

1. Targeting-plate method was used.
2. An acceptable quality limit of 4,0 % is met for a single sampling plan when 29 or more of the 32 tested specimens show "pass" results.

Sample Photo:

Sample Picture (As received)



SGS authenticate the photo on original report only

*** End of Report ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.